



Epoxy Coat™ 7000 AR

Description:	An acid-resistant, room-temperature cured, 100% solids, epoxy coating
Intended Use:	Industrial Use: Ideal coating for chemical storage tanks, dike walls, and containment areas where chemical resistance to acids are needed
Features:	High build (8-10 mils) (0.20-0.25 mm) Superior resistance to concentrated acids (including 98% sulfuric) Applies with brush or roller Excellent adhesion to concrete surfaces Novolac resin
Limitations:	Suitability of product is determined by the end user for their application and process. Not recommended for outdoor use

Typical Physical Properties: Technical data should be considered representative or typical only and should not be used for specification purposes.

Cured 7 Days @ 75°F (24°C)

Hardness
Solids by Volume
Temperature Resistance

Typical Values

85 Shore D
100%
Wet: 130°F (54°C); Dry: 200°F (93°C)

Standard Tests

Shore D ASTM D 2240

Uncured Properties @ 72°F (23°C)

Application Temperature 60-90°F (16-32°C)
Color Gray
Coverage (16 mil / 0.4mm) 100 ft²/Gal (2.5m²/L)
Cure Time 24 hrs
Cure Time - Full Chemical 10 days
Cure Time - Full Service 48 hrs
Functional Cure 24 hrs
Maximum Recoat Time @ 75°F (24°C) 6-8 hrs
Mix Ratio 1.7:1 by weight./1.5:1 by volume
Mixed Viscosity 3,600 cP
Pot Life @ 75°F (24°C) 36 min

Surface Preparation: **Concrete & Masonry:** Begin with a sound, clean, dry and roughened, oil-free application surface, as it is essential to the success and performance of this product. For proper surface preparation, refer to Concrete or Masonry Surface Preparation as detailed by: **SSP/NACE SSPC-SP13/NACE 6**, or **ICRI No. 310.2R**, **CSP 1-3**. for proper surface preparation guidelines. As seen in the Application section below, **a primer sealer is required**.

Atmospheric: SSPC-SP13/NACE 6, or ICRI No. 310.2R, CSP 1-3
Immersion: SSPC-SP13/NACE 6-4.3.1 or 4.3.2 or ICRI No. 310.2R, CSP 1-3

NEW POURED CONCRETE, allow to fully cure (28 days @ 70°F (21°C)) prior to application. Remove any curing membrane by sanding or etching with a strong detergent. Remove any laitance if present.

OLD CONCRETE, thoroughly clean surface with a grease-cutting detergent to remove grease and oils, and remove any loose or unsound concrete by chipping, scarifying, shotblasting, sanding, or grinding. Proceed as for new poured concrete.

PREVIOUSLY COATED CONCRETE, applications should be considered short term because the coating system is only as strong as its weakest component. Remove any peeling or degraded paint by sanding or using a paint stripper. For intact paint, thoroughly clean the surface with a strong detergent, then lightly sand to remove any gloss. Treat any areas worn down to the original concrete as bare concrete.

Metal: If metal is also being coated, **Primer is required**. It is recommended to use a wire brush or sandpaper to remove rust and scale from the surface to be protected. Surfaces may be shot blasted or abraded using a wire wheel for best results. All dirt, grease and old paint should be removed. A clean dry surface is essential for the best results. A metal primer is required and is sold separately. See **SSPC-SP1** or **SSPC-SP10/Nace2** for metal cleaning. Optimal profile 2 mils / 50 microns

Atmospheric: SSPC-SP6/NACE 3, ISO 8501-1 Sa2 ,2 mil (50 micron) profile

Immersion: SSPC-SP10/NACE 2, ISO 8501-1 SA2.5, 2-3 mil (50-75 micron) profile

Mixing Instructions:
1. Pour hardener into resin.
2. Mix for about three (3) minutes using a propeller-type Jiffy Mixer Model ES (or equivalent) until a uniform color is achieved.

Application Instructions:
PRIOR TO APPLICATION:
1. Fill large holes with a patching compound (Devcon Floor Patch or Devcon Ultra Quartz is recommended).
2. Apply the required precoat primer: Sealer 100 (sku# 12540 EMEA) or Concrete Sealer (sku# 12560 Americas) to concrete/cement prepared Surface. See Technical Data Sheets on Sealer 100 and Concrete Sealer for specific product details.

APPLICATION:

Apply Epoxy Coat 7000 AR onto previously applied Concrete Sealer primer with a notched squeegee, then "back roll" for a smooth finish (a 3/8" (9.5 mm) or 0.5 in. (12.5 mm) nap roller is recommended for best results). Coverage will vary based on surface conditions.

After applying the first coat, the need for a second coat can be assessed based on floor condition and end user's objectives. When applying a second layer, the maximum recoat time is 6-8 hours.

Epoxy Coat 7000 AR produces a smooth finish, which can be slippery, especially when wet. To prevent slipping, add a non-skid aggregate, such as ground walnut shells or dry sand, to the coating.

Storage: Store at room temperature. 70°F (21°C).

Compliances: Approved in the U.S. for use in meat and poultry processing plants.
Accepted by Canadian Department of Agriculture Food Safety Service.

Chemical Chemical resistance is calculated with a 7-day, room temp. cure (30 days immersion) @ 75°F (24°C)

Resistance:			
Acetic (Dilute) 10%	Poor	Nitric 50%	Fair
Cutting Oil	Excellent	Phosphoric 50%	Excellent
Gasoline (Unleaded)	Excellent	Potassium Hydroxide 40%	Very good
Methanol	Poor	Sodium Hydroxide 50%	Excellent
Methyl Ethyl Ketone	Poor	Sodium Hypochlorite	Excellent
Hydrochloric 36%	Excellent	Sulfuric 10%	Excellent
Methylene Chloride	Poor	Sulfuric 98%	Excellent
Nitric 10%	Excellent	Toluene	Excellent

Precautions: **FOR INDUSTRIAL USE ONLY:** Please refer to the appropriate Safety Data Sheet prior to using this product.

Warranty: ITW Performance Polymers will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

Order
Information:

Item No.	Package Size
12750	2 gal. (7.56 Liter)

Contacts: www.itwpp.com

ITW Performance Polymers (EMEA) Bay 150, Shannon Industrial Estate Shannon, County Clare, Ireland V14 DF82 TEL: +353 61 771 500 FAX: +353 61 471 285 Email: customerservice.shannon@itwpp.com	ITW Performance Polymers (US) 30 Endicott Street Danvers, MA 01923 USA TEL: 855 489 7262 FAX: 978 774 0516 Email: info@itwpp.com
--	---

Disclaimer: **Product Use:** The information herein is based upon good faith testing that ITW PP believes are reliable, but the accuracy or completeness of such information is not guaranteed. Many factors beyond ITW PP control and uniquely within user's knowledge and control can affect the use and performance of an ITW PP product in a particular application. Given the variety of influencers on performance, the data here is not intended to substitute end user testing. It is the end users sole responsible for evaluating any ITW PP product and determining whether it is fit for a particular purpose and suitable for user's design, production, and final application.

Exclusion of Warranties: As to the herein described materials and test results, there are no warranties which extend beyond the description on the face hereof. ITW PP makes no other warranties, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose. Since the use of the herein described involves many variables in methods of application, design, handling and/or use, the user, in accepting and using these materials, assumes all responsibility for the end result. ITW PP shall not otherwise be liable for loss of damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability.